


ARTISAN CHIMAY

Limestone Floor & Wall Tile




Faro
8" x 16" x 5/8"
IMP8X16FA



Faro
16" x 24" x 5/8"
IMP16X24FA



Chimay
8" x 16" x 5/8"
IMP8X16CH




Chimay
16" x 24" x 5/8"
IMP16X24CH

TECHNICAL SPECIFICATIONS

PRODUCT PERFORMANCE	RESULT
Flexural Strength	EN 12372 Average Value=16.2 Mpa Min. Expected Value=13.6 Mpa Standard Deviation=1.8 Mpa
Slip Resistance	Dry Conditions Avg Value=137 SRV Wet Conditions Avg Value=38 SRV
Abrasion Resistance	EN 14157 Average Value=19.9 mm
Frost Resistance	EN 12371 No changes after 48 test cycles
Fire Behavior	EN 13501-1 Class A1
Recommended Grout Joint	1/8"-1/4"
Color Shade Variation	V4
Open Porosity	EN 1936 Average Value=1.4% Standard Deviation=0.3%

View all of our product options and detailed specifications at:
mlwsurfaces.com



Orval
8" x 16" x 5/8"
IMP8X16OR



Orval
16" x 24" x 5/8"
IMP16X24OR



GET IN TOUCH

✉ orders@mlwalker.com


📍 3045 Kingston Court
Norcross, GA 30071

🌐 www.mlwsurfaces.com

mlwsurfaces

ARTISAN FARO


Limestone Floor & Wall Tile



Faro
8" x 16" x 5/8"
IMP8X16FA



Faro
16" x 24" x 5/8"
IMP16X24FA



Chimay
8" x 16" x 5/8"
IMP8X16CH




Chimay
16" x 24" x 5/8"
IMP16X24CH

TECHNICAL SPECIFICATIONS

PRODUCT PERFORMANCE	RESULT
Water Absorption	EN 13755 Average value=1.00% Max. expected value=1.08% Standard Deviation=0.04%
Flexural Strength	EN 12372 Average Value=16.37 Mpa Min. Expected Value=11.06 Mpa Standard Deviation=3.0 Mpa
Wear Resistance	EN 14157 Mean Value=17.12 Max. Expected Value=18.32 Standard Deviation=0.81
Frost Resistance	EN12371 No changes after 72 test cycles
Recommended Grout Joint	1/8"-1/4"
Color Shade Variation	V4

View all of our product options and detailed specifications at:
mlwsurfaces.com



Orval
8" x 16" x 5/8"
IMP8X16OR



Orval
16" x 24" x 5/8"
IMP16X24OR



GET IN TOUCH

✉ orders@mlwalker.com


📍 3045 Kingston Court
Norcross, GA 30071

🌐 www.mlwsurfaces.com

mlwsurfaces

ARTISAN ORVAL


Limestone Floor & Wall Tile



Faro
8" x 16" x 5/8"
IMP8X16FA



Faro
16" x 24" x 5/8"
IMP16X24FA



Chimay
8" x 16" x 5/8"
IMP8X16CH




Chimay
16" x 24" x 5/8"
IMP16X24CH

TECHNICAL SPECIFICATIONS

PRODUCT PERFORMANCE	RESULT
Flexural Strength	EN 12372 Average Value=18.1 Mpa Min. Expected Value=16.2 Mpa Standard Deviation=0.9 Mpa
Slip Resistance	Dry Conditions Mean Value=49 SRV Wet Conditions Avg Value=7 SRV
Abrasion Resistance	EN 14157 Average Value=23.5 mm Max. Expected Value=25.5mm Standard Deviation=0.7mm
Frost Resistance	EN 12371 No changes after 48 test cycles
Fire Behavior	EN 13501-1 Class A1
Recommended Grout Joint	1/8"-1/4"
Color Shade Variation	V4
Open Porosity	EN 1936 Average Value=4.4% Standard Deviation=0.1%
Apparent Density	EN 1936 Average Value=2560 kg/ ³ Standard Deviation=10 kg/ ³

View all of our product options and detailed specifications at:
mlwsurfaces.com



Orval
8" x 16" x 5/8"
IMP8X16OR



Orval
16" x 24" x 5/8"
IMP16X24OR



GET IN TOUCH

✉ orders@mlwalker.com

📍 3045 Kingston Court
Norcross, GA 30071

🌐 www.mlwsurfaces.com

mlwsurfaces